

Reaction to fire classification according to EN 45545-2

(1 appendix)

Introduction

This classification report defines the reaction to fire classification assigned to the product called “Moniflex” in accordance with EN 45545-2:2013+A1:2015. Test reports and test results in support of classification, together with the classification criteria, are presented in appendix 1.

Product description

According to the client: Thermal acoustic insulation called “Moniflex”, consisting of layers of pleated sheets of FR cellulose acetate. The product has a nominal thickness of 10 – 60 mm, a nominal density of 13 kg/m³ and the colour is transparent. Detailed product description is filed at RISE.

According to the standard EN 45545-2, table 2, the product is defined as a “Listed Product” to which the following parameters apply:

Product No: IN15
Location: Interior
Description: Interiors
Product name: Floor composites
Requirement Set: R10

Basis for classification

A complete series of tests have been performed on the thickness with the poorest results in each test method. Indicative single tests have been performed on the other thickness.

According to paragraph 4.2 in EN 45545-2, products meeting the requirements at the maximum testable thickness shall be considered to comply with the requirement at greater thicknesses.

Classification

The product described above, in relation to its reaction to fire behaviour, is classified according to EN 45545-2:2013+A1:2015, Requirement Set R10; Hazard Levels HL1, HL2 and HL3.

Reaction to fire classification: R10; HL1/HL2/HL3

RISE Research Institutes of Sweden AB

Postal address	Office location	Phone / Fax / E-mail
Box 857	Brinellgatan 4	+46 10 516 50 00
SE-501 15 BORÅS	SE-504 62 BORÅS	+46 33 13 55 02
Sweden		info@ri.se

This document may not be reproduced other than in full, except with the prior written approval of RISE.

Field of application

This classification is valid for the following product parameters:

Nominal thickness: 10 – 60 mm.

Nominal density: 13 kg/m³.

This classification is valid for the following end use conditions:

Substrates

- Steel sheet with nominal thickness $\geq 0.8 \pm 0.2$ mm.

Limitations

This classification document does not represent type approval or certification of the product.

The sample was delivered by the client. RISE Safety – Fire Research was not involved in the sampling procedure.

**RISE Research Institutes of Sweden AB
Safety - Fire Research Materials**

Performed by

Examined by

Anna Bergstrand

Per Thureson

Appendix

1. Basis for fire classification



Appendix 1

Basis for fire classification

1 Test reports & test results in support of classification

1.1 Test reports

This classification, according to EN 45545-2, is based on the test reports:

Laboratory	Sponsor	Test report no	Accredited test method
RISE	Isoflex AB	8P02524-9	EN ISO 9239-1
RISE	Isoflex AB	8P02524-10	EN ISO 5659-2+ EN 45545-2, annex C

1.2 Test results

Mean values of the test results are summarized:

<i>Test method</i>	<i>Number of tests</i>	Parameter	Results, mean value	Compliance with Requirement Set; Hazard Level
EN ISO 9239-1 (ref. 8P02524-9)	3			
Critical Flux at Extinguishment		CHF	11 kW/m ²	R10; HL1/HL2/HL3
ISO 5659-2: 25 kW/m ² with pilot burner (ref. 8P02524-10)	3			
Maximum specific optical density of smoke		D _s max	42	R10; HL1/HL2/HL3
Conventional index of toxicity, General products		CIT _G	0.01	R10; HL1/HL2/HL3

2 Reaction to Fire Classification

2.1 Reference for classification

According to EN 45545-2 “Railway applications – Fire protection on railway vehicles – Part 2: Requirements for fire behaviour of materials and components”, to meet the set of material requirements according to table 5, requirement set R10, the product must fulfil the classification criteria for each test method tested as described below.

Appendix 1

2.2 Classification criteria

Classification criteria according to Requirement Set R10 are summarized as follows:

<i>Test method</i>	HL1	HL2	HL3
<i>ISO 9239-1</i>			
Critical Heat Flux, CHF	≥ 4.5	≥ 6	≥ 8
<i>ISO 5659-2: 25kW/m², with pilot flame</i>			
Maximum specific optical density of smoke, D _s max	≤ 600	≤ 300	≤ 150
Conventional index of toxicity, General products, CIT _G	≤ 1.2	≤ 0.9	≤ 0.75